


- Standard application UL224, CAN/ CSAC22.No198.1-99
- Halogen free, low smoke, soft and easy to take
- RoHS compliant
- Different color available



Part number

PR-HST-XXxXX-XX-XXXX				
PR	HST	XXxXX	XX	XXXX
NA	Type indicates	Diameter indicates Before and after shrink	Color indicates	Length indicates
Default	General type	Unit mm	BK=Black BU=Blue YG=Yellow/Green RD=Red GN=Green ...	Default by meter Special length cut as unit mm

General dimensions

Shrink ratio 2:1		Shrink ratio 3:1		Shrink ratio 4:1	
Inside diameter before shrinkage (D) mm	Inside diameter after shrinkage(d) mm	Inside diameter before shrinkage (D) mm	Inside diameter after shrinkage(d) mm	Inside diameter before shrinkage (D) mm	Inside diameter after shrinkage(d) mm
6.0	3.0	3.0	1.0	4.0	1.0
8.0	4.0	4.8	1.6	6.0	1.5
10.0	5.0	6.4	2.2	8.0	2.0
12.0	6.0	7.9	2.7	10.0	2.5
13.0	6.5	9.5	3.2	12.0	3.0
14.0	7.0	12.7	4.2	16.0	4.0
16.0	8.0	15.0	5.0	19.0	4.5
18.0	9.0	19.1	6.3	25.0	6.5
20.0	10.0	25.4	8.5	30.0	7.5
25.0	12.5	30.0	10.0	38.0	9.5
30.0	15.0	39.0	13.0	51.0	13.0
35.0	17.5	50.0	16.0		
40.0	20.0	64.0	21.0		
50.0	25.0	75.0	25.0		
60.0	30.0	90.0	30.0		

Material

Material	Polyolefin
----------	------------

Electrical data

Rating voltage	300V
Dielectric withstander voltage	1500V, 1min not break
Volume resistivity	$\geq 10^{14} \Omega \cdot \text{cm}$

Mechanical data

Tensile strength	$\geq 10.4 \text{MPa}$
Elongation at break	$\geq 200\%$

Environment

Working temperature	-55°C to +105°C
Start to shrink	$\geq 70^\circ\text{C}$
Flame retardant	VW-1
RoHS	Compliant

While the information has been carefully compiled to the best of our knowledge, nothing is intended as representation or warranty on our part and no statement herein shall be construed as recommendation to infringe existing patents. In the effort to improve our products, we reserve the right to make changes judged to be necessary.